



Glue-down Luxury Vinyl Flooring Spec Sheet

Version North America

Origin China

SPECIFICATIONS

Product type	LVT	Installation	Glue-down
Overall thickness	2.5mm	Bevel	Cut bevel on 4 sides
Wear layer	20mil (0.5mm)	Finish	UV coating

INGREDIENTS AND EMISSIONS

VOC Certifications GreenGuard Gold (Compliant)

Norm	Item	Test Method	Requirement	Result
CPSIA & Prop 65	Ortho-Phthalates	CPSC-CH-C-1001-09.4	N.D.	Compliant
	Heavy metals	ASTM F963	See the standard for details	Compliant
REACH	SVHC	Spectrometry, chromatography	≤0.1%	Compliant

PERFORMANCE

Norm	Item	Test Method	Requirement	Result
ASTM F1700	Length tolerance	ASTM F2055	+/- 0.4 mm per 305mm	Compliant
	Width tolerance	ASTM F2055	+/- 0.4 mm per 305mm	Compliant
	Thickness tolerance	ASTM F386	+/- 0.15mm	Compliant
	Thickness of wear layer	ASTM F410	commercial, 0.020 in. (0.5 mm) min	Compliant
	Squareness	ASTM F2055	0.25mm	Compliant
	Residual indentation	ASTM F1914	≤8% (140lbs/63.5kg)	Compliant
	Flexibility	ASTM F137	No cracks or breaks	Compliant
	Dimensional stability	ASTM F2199	ΔW/ΔL ≤ 0.17%	Compliant
	Resistance to chemicals	ASTM F925	Slight change only	Compliant
	Resistance to heat	ASTM F1515	ΔE ≤8	Compliant
NALFA LF 01-2011	Resistance to light	ASTM F1514	ΔE ≤8	Compliant
	Impact resistance	NALFA LF 01-2019 3.5	≥ 1400mm	Compliant
	Impact resistance	NALFA LF 01-2019 3.6	≥ 500mm	Compliant

LEED SCORECARD

How our products fit into LEED v4:

LEED BD+C and ID+C	Credit Type	Points	Criteria	Product Contribution
EQ Credit: Low-Emitting Materials	EQ Credit: Low-Emitting Materials	1-3 points	Option 1. Product has been tested according to California Department of Public Health (CDPH) Standard Method v1.2–2017 and complies with the VOC limits in Table 4-1 of the method. Additionally, the range of total VOCs after 14 days (336 hours) was measured as specified in the CDPH Standard Method v1.2 and is reported (TVOC ranges: 0.5 mg/m3 or less, between 0.5 and 5 mg/m3, or 5 mg/m3 or more).	CFL LVT products are GreenGuard Gold certified.
			Option 2. Product has been tested according to EN 16516:2017 and complies with the LCI values from Table 1 of the German AgBB Testing and Evaluation Scheme (2015) and a formaldehyde limit of 10 micrograms per cubic meter. Additionally, the range of total VOCs after 28 days was measured as specified in EN 16516 and reported (TVOC ranges: 0.5 mg/m3 or less, between 0.5 and 5 mg/m3, or 5 mg/m3 or more).	CFL LVT products are IAC Gold compliant, including compliance with German AgBB testing.
MR Credit: Building Product Disclosure and Optimization – Material Ingredients	MR Credit: Building Product Disclosure and Optimization – Material Ingredients	1 point	Option 1. Material Ingredient Optimization International Alternative Compliance Path – REACH Optimization (value at 100% of cost or 1 product). End use products and materials have fully inventoried chemical ingredients to 100 ppm and assess each substance against the Authorization List – Annex XIV, the Restriction list – Annex XVII and the SVHC candidate list, (the version in effect June 2013,) proving that no such substance is included in the product. If the product contains no ingredients listed on the REACH Authorization, Restriction, and Candidate list.	CFL LVT products are REACH compliant.

WELL SCORECARD

The WELL Building Standard is founded on the understanding that facets of our environment interact with personal, genetic and behavioral factors to shape our overall health and well-being. By compiling leading practices in building design and management and referencing existing standards and best practice guidelines set by governmental and professional organizations, WELL works to harmonize and clarify existing thresholds and requirements.

Facet	Feature	Part	Requirements	Concept score	How our product contribute to obtain WELL level certification
AIR	01. Air quality standards	1. Standards For Volatile Substances	The following conditions are met: a. Formaldehyde levels less than 27ppb (0.027ppm) b. Total volatile organic compounds less than 500ug/m3 (0.5mg/m3)	PRECONDITION	a. Formaldehyde emission are less than 0.05mg/m3. b. The total volatile organic compounds are less than 0.5mg/m3.

04. VOC Reduction	1. Interior Paints and Coatings	The VOC limits of newly applied paints and coating meet one of the following requirements: a. 100% of installed products meet California Air Resources Board (CARB) 2007, Suggested Control Measure (SCM) for Architectural Coatings, or South Coast Air Quality Management District (SCAQMD) Rule 1113, effective June 3, 2011 for VOC content. b. At minimum 90%, by volume, meet the California Department of Public Health (CDPH) Standard Method v1.1-2010 for VOC emissions	PRECONDITION	a. The VOC limits for California Air Resources Board (CARB) are less than 0.11ppm. b. Measured Concentration of Total Volatile Organic Compounds (TVOC): Less than/equal to 0.5 mg/m ³ (in compliance with CDPH/EHLB Standard Method v1.1-2010). The product is GreenGuard Gold certified
	3. Flooring	The VOC emissions of all newly installed flooring must meet all limits set by the following, as applicable: a. California Department of Public Health (CDPH) Standard Method v1.1-2010.	PRECONDITION	Conforms to the CDPH/EHLB Standard Method v1.1-2010 (California Section 01350), effective January 1, 2012, for the school classroom and private office parameters when modeled as Flooring. The product is GreenGuard Gold certified
11. Fundamental Material Safety	1. Asbestos and Lead Restriction	All newly-installed building materials meet the following materials composition requirements: a. No asbestos. b. Not more than 100 ppm (by weight) added lead.	PRECONDITION	a. No asbestos b. The product contain less than 100 ppm.
	2. Lead Abatement	For repair, renovation or painting on buildings constructed prior to any applicable laws banning or restricting lead paint, lead evaluation and abatement.	PRECONDITION	The product contain less than 90 ppm.
	3. Asbestos Abatement	To reduce hazards in buildings constructed prior to any applicable laws banning or restricting asbestos, the following testing, evaluation and abatement.	PRECONDITION	The product contain less than 90 ppm.
25. Toxic Material Reduction	2. Flame Retardant Limitation	Halogenated flame retardants are limited in the following components to 0.01% (100 ppm) to the extent allowable by local code: a. Window and waterproofing membranes, door and window frames and siding. b. Flooring, ceiling tiles and wall coverings. c. Piping and electrical cables, conduits and junction boxes. d. Sound and thermal insulation. e. Upholstered furniture and furnishings, textiles and fabrics.	OPTIMIZATION	The product don't contain halogenated flame retardants
	3. Phthalate (Plasticizers) Limitation	DEHP, DBP, BBP, DINP, DIDP or DNOP (often found in polyvinyl chloride [PVC]) are limited in the following components to 0.01% (100 ppm): a. Flooring, including resilient and hard surface flooring and carpet. b. Wall coverings, window blinds and shades, shower curtains, furniture and upholstery. c. Plumbing pipes and moisture barriers.	OPTIMIZATION	In accordance with US Consumer Product Safety Improvement Act 2008 (CPSIA) (H.R.4040) Title I, Section 108 & California Proposition 65 & Annex XV II item 51&52 of the REACH Regulation (EC) No. 1907/2006 and amendment No. 552/2009, the product contains less than 100ppm.
	5. Urea-Formaldehyde Restriction	Urea-formaldehyde presence is limited in the following components to 100 ppm: a. Furniture or any composite wood products. b. Laminating adhesives and resins. c. Thermal insulation.	OPTIMIZATION	The product contains urea-formaldehyde less than 100ppm.

END OF DOCUMENT
